



Evaluation of a Conductive Elastomer Seal for Spacecraft

Christopher C. Daniels, Janice L. Mather, and Heather A. Oravec
The University of Akron, Akron, OH

Patrick H. Dunlap, Jr. (presenter)
NASA Glenn Research Center, Cleveland, OH

52nd AIAA/SAE/ASEE Joint Propulsion Conference
Salt Lake City, UT
July 27, 2016



Introduction

- Future spacecraft will require gas pressure seals with very low leak rates
- Some locations on vehicle outer mold line (e.g., doors, hatches, access panels) also require low impedance between metal interfaces
 - Provides fault current path to protect personnel from electrical shock
 - Protects equipment from lightning strikes
- Class L electrical bonding requirements necessitate direct current resistance between metal interfaces of 2.5 milliohms or less for protection from lightning strikes
- Gas pressure seal that provides continuous, low-resistance electrical pathway is desirable
- Electrically conductive elastomer was evaluated as potential material for future spacecraft seals



Orion spacecraft




Testing


- Performed a series of tests to evaluate material properties and performance characteristics:
 - Outgassing
 - Electrical resistivity
 - Compression set
 - Compression and adhesion forces
 - Leak rate

Test Articles

- Seal material:
 - CHO-SEAL® 1285 compound manufactured by Parker Hannifin Corporation's Chomerics Division (Woburn, MA)
 - Contains silver-plated aluminum in a silicone matrix
- Specimen geometry:
 - Hollow O-ring
 - Nominal cross section dimensions:
 - 6.60 mm (0.260 in.) inner diameter
 - 11.1 mm (0.438 in.) outer diameter
 - Different specimen lengths used for different types of tests



Hollow O-ring design used for testing



Test articles used for different tests:
(a) electrical resistivity, compression force, & adhesion force, (b) compression set, (c) leak rate




Outgassing Tests

- Elastomers can release products (especially under vacuum) that condense on other nearby surfaces
- Seal outgassing contaminants must be minimized so they do not compromise functionality of surfaces with highly controlled optical properties (e.g., windows, lenses, solar arrays)
- Objective: Measure outgassing properties of CHO-SEAL® 1285 compound
- Test details:
 - Three samples cut from linear segment of hollow O-ring
 - Average sample mass of 225 mg
 - Tests conducted per ASTM E595-07
- Results:
 - Compound met outgassing requirements for spacecraft materials with total mass loss (TML) less than 1.0% and collected volatile condensable materials (CVCM) value less than 0.1%

	Measurement	Requirement
TML, %	0.041	Less than 1.0
CVCM, %	0.014	Less than 0.1

Electrical Resistivity Measurements

- Objective: Measure electrical resistance of structural joint formed by seal compressed between two platens
- Test details:
 - 62.2 cm linear segment of hollow O-ring was compressed between two platens made of aluminum coated with electroless nickel (0.008 to 0.01 mm thick; class 4, grade A per SAE-AMS-C-26074)
 - Only conductance path was through test article
 - Resistance measured by milliohm meter through electrical leads connected to upper and lower platens
 - Measurements were made at three compression levels by applying additional weight to upper platen:
 - Upper platen by itself (91 N)
 - Upper platen plus 45 N
 - Upper platen plus 89 N



Hardware setup for electrical resistivity measurements



Electrical Resistivity Measurements (cont.)

Configuration (total force)	Resistance, milliohms
Upper platen only (91 N)	0.70
Upper platen plus 45 N (136 N)	0.66
Upper platen plus 89 N (180 N)	0.62

- Results:
 - Electrical resistance of assembly decreased slightly as more weight was applied to upper platen
 - All tested assemblies met Class L electrical bonding requirement of 2.5 milliohms or less
 - Results suggest that elastomer is capable of conducting electrical charge with minimal resistance
 - However, actual resistance for potential spacecraft seal application will be dependent on seal length and cross section dimensions

Compression Set Measurements

- Seals must remain in contact with adjacent sealing surfaces to form an effective seal
- However, elastomer seals can take on permanent deformation (i.e., “set”) after they are compressed, especially for long period of time
- Objective: Measure permanent deformation of seal after force is applied for a period of time and then removed
- Test details:
 - Two lots of three specimens each: with and without vacuum grease
 - Followed ASTM D395 Method B guidelines with minimal exceptions
 - Compressed specimens at room temperature for 70 hrs between two steel platens
 - Used spacers to compress test articles to 75% of average pre-test height



Test articles (4 cm long) arranged on steel platen with spacers before 70 hr compression hold



Compression Set Measurements (cont.)

- Measurements & calculations:

- Measured test article heights before and after using non-contact laser profile measurement system
- Recorded average of four measurements for each test article
- Reported final compression set measurement as median value from three test articles in each lot

$$\frac{h_o - h_{70}}{h_o - h_{spacer}} * 100$$


- Results:

- Lubricated test articles exhibited less compression set; allowed for greater deformation and reduced stress
- Compression set values were higher than those for other silicone elastomers (typically 5-11%)
- Compression set must be evaluated for longer durations and at representative temperatures before using this compound in space seal applications

	Unlubricated	Lubricated
Compression set measurement	15.3%	14.0%

Compression & Adhesion Force Measurements


- Objectives:
 - Measure force required to compress the seal
 - Measure force required to separate seal from opposing sealing surface
- Test details:
 - Tested seal at 18.3°C in test fixture installed in Instron electromechanically actuated load frame
 - Seal was installed in dovetail groove and compressed against flat plate
 - Plates made of aluminum with clear anodized finish per MIL-A-8625, Type II, Class 1
 - Fully compressed seal for 10 load cycles
 - Compress at 0.2 mm/sec
 - 1 minute hold
 - Separate at 0.25 mm/sec
 - 1 minute recovery



Test setup for seal compression & adhesion force measurements



Compression Force Measurements




Cycle number	Compression force, N/cm	Uncertainty, N/cm
1	15.1	±2.5
2	14.5	±2.5
3	14.2	±2.5
4	14.0	±2.5
5	13.5	±2.5
6	13.8	±2.5
7	13.5	±2.5
8	13.7	±2.5
9	13.7	±2.5
10	13.7	±2.5

- Force required to compress seal decreased slightly with load cycling
- Relatively soft elastomer compound and hollow O-ring design resulted in low forces to compress seals when compared to solid seal designs made of higher durometer materials
- Additional testing would be required to evaluate compression force response over time and at representative operating temperatures



Adhesion Force Measurements



Cycle number	Adhesion force, N/cm	Uncertainty, N/cm
1	-0.08	+0.08 / -0.6
2	-0.07	+0.08 / -0.6
3	-0.08	+0.08 / -0.6
4	-0.07	+0.08 / -0.6
5	-0.07	+0.08 / -0.6
6	-0.08	+0.08 / -0.6
7	-0.07	+0.08 / -0.6
8	-0.07	+0.08 / -0.6
9	-0.08	+0.08 / -0.6
10	-0.07	+0.08 / -0.6

- Force required to separate seal from sealing surface (i.e., seal adhesion) was very low and not significantly different than zero
- Desirable characteristic → minimizes need for mechanism to separate the joint
- Additional testing would be required for longer hold durations and at representative operating temperatures

Leak Rate Measurements

- Objective: Measure seal leak rates
- Test details:
 - Tested seal at 23 and 61°C in test fixture installed in environmental control chamber to maintain constant test temperature
 - Seal was installed in dovetail groove and compressed against flat plate
 - Plates made of aluminum with clear anodized finish per MIL-A-8625, Type II, Class 1
 - Pressurized volume inboard of seal to 129 kPa
 - Controlled pressure in volume downstream of seal (low-pressure side) to maintain constant differential pressure across seal of 101 kPa throughout test
 - Used mass point leak rate method to analyze data and obtain leak rate results and uncertainty





Diagram of leak rate measurement test apparatus



Leak Rate Measurements (cont.)



Temperature, °C	Leak rate, ng/s	Uncertainty, ng/s
23	258	4.08
61	358	3.28

- Results:
 - Leak rate increased at warmer test temperature
 - Leak rates were higher than those for other seals used for space applications but still reasonable
 - Void in hollow O-ring provided no resistance to flow
 - Force required to compress seal was low; allowed for increased leakage through interfaces between seal and sealing surfaces



Summary

- Electrically conductive elastomer was evaluated as potential material for future spacecraft seals
- Compound met outgassing requirements for spacecraft materials with TML less than 1.0% and CVCM less than 0.1%
- All tested assemblies met Class L electrical bonding requirement of 2.5 milliohms or less
- Hollow O-ring seal made of candidate compound required low forces to compress it but exhibited higher compression set values than those for other silicone elastomers
- Seal exhibited very low, near-zero adhesion forces
- Leak rates were higher than those for other seals used for space applications but still reasonable
- Overall, compound shows promise as potential material for spacecraft seals, but additional testing should be performed under representative operating conditions (e.g., temperatures) and for longer durations before implementation



Acknowledgments

- The authors would like to thank:
 - Nathan Williams for assistance with electrical resistance measurements
 - John Mayer and Joseph Assion from Vantage Partners, LLC for engineering design support
- Funding for this work was provided by NASA under contract NNC13BA10B